



ROWOSHIELD® ROS-M1

Conductive woven for shielding electro-magnetic radiation

Technical specification

Substrate:	Polyester ripstop woven
Weight:	77 g/m ² ± 4 g/m ²
Width:	1.340 mm ± 40 mm
Coating:	Copper + corrosion resistant coating
Sheet resistance:	< 15 mΩ/□
Shielding effectiveness:	78 –93 dB from according to 0,01 – 4 GHz ASTM D-4935-89 (certificate available)

For more information:

ROWO Coating
Gesellschaft für Beschichtung mbH
Allmendstr. 7
79336 Herbolzheim
Tel.: 07643-40015 Fax: 07643-40159
e-Mail: wolfgang.siefert@rowo-coating.de