



ROWOSHIELD® ROS-M4

Conductive nonwoven for shielding of electro-magnetic radiation

Technical specification

Substrate:	Polyester spunbond nonwoven
Weight:	85 g/m ² ± 5 g/m ²
Width:	1.500 mm ± 50 mm
Coating:	Copper + corrosion resistant coating
Sheet resistance:	≤ 10 mΩ/□
Shielding effectiveness:	78 – 88 dB from according to 30 kHz – 4 GHz ASTM D-4935-89

For more information:

ROWO Coating
Gesellschaft für Beschichtung mbH
Allmendstr. 7
79336 Herbolzheim
Tel.: 07643-40015 Fax: 07643-40159
e-Mail: wolfgang.siefert@rowo-coating.de