



ROWOSHIELD® ROS-M5

Conductive nonwoven for shielding electro-magnetic radiation

Technical specification

Substrate:	Polyester spunbond nonwoven
Weight:	42 g/m ² ± 3 g/m ²
Width:	1.500 mm ± 50 mm
Coating:	Aluminium
Sheet resistance:	≤ 0,3 Ω/□
Shielding effectiveness:	47 – 50 dB from according to 0,01 – 4 GHz ASTM D-4935-89 (certificate available)

For more information:

ROWO Coating
Gesellschaft für Beschichtung mbH
Allmendstr. 7
79336 Herbolzheim
Tel.: 07643-40015 Fax: 07643-40159
e-Mail: wolfgang.siefert@rowo-coating.de